



Polypropylene Splicing Tape

Backing Carrier: Unoriented Polypropylene

Adhesive AS/LS: Acrylic

Note: Colors: Clear

Applications

- Containment wrap during the encapsulation of telecommunications splices in the field

Features	Benefits
Unoriented Polypropylene Film	• Strong and rigid • Easy to apply in the field
Acrylic Adhesive	• Excellent quick stick and shear strength • Excellent temperature resistance

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness	6 mils	0.1524 mm	PSTC-133
Carrier Thickness	5 mils	0.127 mm	PSTC-133
Adhesion to Steel	60 oz/in	6.564 N/cm	ASTM D-3330
Tensile Strength	30 lb/in	52.5384 N/cm	ASTM D-3759
Elongation	8		
Application Temperature	40 to 120 °F	4 to 49 °C	
Operating Temperature	-40 to 200 °F	93 °C	
Recommended Storage Temperature	60 to 80 °F	15.6 to 26.7 °C	
Recommended Storage Humidity	40 to 60 %		
Shelf Life (Standard)	12 months from shipment date		

Values shown are based on laboratory testing and represent typical product characteristics. Actual performance will vary depending on application conditions, and no guarantee of performance is made. The user is responsible for determining suitability for the intended application. No express or implied warranty, including merchantability or fitness for a particular purpose, is made.