



Backing Carrier: 0.5 mil PET Film
Adhesive (Air Side): Rubber (I917)
Adhesive (Liner Side): Rubber (I915)
Release Liner: 60# Polycoated Kraft
Specifications: Chrysler

Applications

- Bonding to a wide variety of PU and PE foams, felt, cork, rubber, and sponge materials
- Weatherstripping
- Gasket, insulation, light shielding, and sound damping uses
- Splicing applications
- General purpose bonding uses

Features

Benefits

Differential Rubber Adhesive System

- Air-side offers exceptional high tack
- Liner-side well-suited for general purpose use

Polyester Film Carrier

- Support for aid in processing and application
- Conformable

60# Polycoated Kraft Liner

- Excellent lay flat properties
- Clean die-cuts

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness (with Liner)	7.7 mils	0.196 mm	PSTC 133
Carrier Thickness	0.5 mils	0.013 mm	PSTC 133
Adhesive Thickness (Air Side)	1.4 mils	0.036 mm	PSTC 133
Adhesive Thickness (Liner Side)	1.3 mils	0.033 mm	PSTC 133
Liner Thickness	4.5 mils	0.114 mm	PSTC 133
Adhesion to Steel (Air Side)	145 oz/in	15.86 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (Liner Side)	125 oz/in	13.68 N/cm	PSTC 101 Mod - 1 mil PET
Static Shear (1" x 1" x 1 kg)	>24 Hours		
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	30 to 150 °F	-1 to 66 °C	
Recommended Storage Temperature	60 to 80 °F	15.6 to 26.7 °C	
Recommended Storage Humidity	40 to 60 %		
Shelf Life (Standard)	12 Months		

Values shown are based on laboratory testing and represent typical product characteristics. Actual performance will vary depending on application conditions, and no guarantee of performance is made. The user is responsible for determining suitability for the intended application. No express or implied warranty, including merchantability or fitness for a particular purpose, is made.