



Backing Carrier: 0.5 mil PET Film
Adhesive AS/LS: Rubber (I918)
Release Liner: 74# Polycoated Kraft

Applications

- Extremely aggressive for bonding to a broad variety of substrates

Features	Benefits
Rubber-Based Adhesive	- Exceptional peel strength - High tack and good shear properties
Polyester Film Carrier	- Support for aid in processing and application - Conformable
74# Kraft Liner	Conformable and good dimensional stability

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness (with Liner)	11 mils	0.279 mm	PSTC 133
Carrier Thickness	0.5 mils	0.013 mm	PSTC 133
Adhesive Thickness (Air Side)	2.5 mils	0.064 mm	PSTC 133
Adhesive Thickness (Liner Side)	2.5 mils	0.064 mm	PSTC 133
Liner Thickness	5.5 mils	0.14 mm	PSTC 133
Adhesion to Steel (Air Side)	190 oz/in	20.806 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel (Liner Side)	185 oz/in	20.239 N/cm	PSTC 101 Mod - 1 mil PET
Static Shear (1" x 1" x 1 kg)	14 Days		
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	30 to 150 °F	-1 to 66 °C	
Recommended Storage Temperature	60 to 80 °F	15.6 to 26.7 °C	
Recommended Storage Humidity	40 to 60 %		
Shelf Life (Standard)	12 Months		

Values shown are based on laboratory testing and represent typical product characteristics. Actual performance will vary depending on application conditions, and no guarantee of performance is made. The user is responsible for determining suitability for the intended application. No express or implied warranty, including merchantability or fitness for a particular purpose, is made.