



Clear Butyl Window & Door Flashing Tape

- Backing Carrier:** Woven Polyethylene (Unprinted or Printed)
- Adhesive:** Clear Butyl Rubber
- Release Liner:** PET Film
- Standard Colors:** Gray, White
- Specifications:** Listed on AAMA's Verified Components List for AAMA 711-22
- Note:** Listed on AAMA's Verified Components List for AAMA 711-20
- Standard Sizes:** 4" x 75Ft, 6" x 75Ft, 9" x 75Ft, 12" x 75ft

Applications

- Window and door installations
- Side-wall sheathing seams
- Sealing other detail areas against water and air penetration
- Corner board abutments
- Deck-to-wall joints

Features

Benefits

Woven Polyethylene Backing

- Conformable and durable
- Excellent air and moisture barrier properties
- Suitable for up to 1 year outdoor UV exposure

Clear Butyl Rubber Adhesive

- Provides permanent weather-tight seal on most clean, dry building surfaces
- Excellent cold temperature adhesion
- Compatible with sealants and caulking
- Self-healing after puncture
- Used properly, can contribute toward requirements for EA Credit 1 (Optimize Energy Performance) under LEED®

PET Film Liner

- Easy to remove

Values shown are based on laboratory testing and represent typical product characteristics. Actual performance will vary depending on application conditions, and no guarantee of performance is made. The user is responsible for determining suitability for the intended application. No express or implied warranty, including merchantability or fitness for a particular purpose, is made.



Clear Butyl Window & Door Flashing Tape

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness (without Liner)	14.5 mils	0.37 mm	ASTM D-1000
Adhesion to Backing	104 oz/in	11.38 N/cm	ASTM D3330 Method F
Adhesion to Vinyl	115 oz/in	12.58 N/cm	ASTM D3330 Method F
Adhesion to Aluminum	122 oz/in	13.35 N/cm	ASTM D3330 Method F
Adhesion to Plywood	107 oz/in	11.71 N/cm	ASTM D3330 Method F
Adhesion to OSB	96 oz/in	10.5 N/cm	ASTM D3330 Method F
Tensile Strength (Machine Direction)	2855 PSI		ASTM D 1970 Sec 7.3
Tensile Strength	52 lb/in		ASTM D3759 Procedure A
Elongation	36 %		ASTM D3759 Procedure A
Installation Temperature	176 °F	-23 to 80 °C	
Operating Temperature	-30 to 200 °F	-34 to 93 °C	
Recommended Storage Temperature	60 to 80 °F	15.6 to 26.7 °C	
Recommended Storage Humidity	40 to 60 %		
Shelf Life (Standard)	36 Months		

Values shown are based on laboratory testing and represent typical product characteristics. Actual performance will vary depending on application conditions, and no guarantee of performance is made. The user is responsible for determining suitability for the intended application. No express or implied warranty, including merchantability or fitness for a particular purpose, is made.