



Low VOC & LSE Acrylic Transfer Tape



Adhesive:	Acrylic (I626)
Release Liner:	74# Polycoated Kraft
Specifications:	Passes Automotive Fogging Test: SAE J1756 @ 100 °C as tested Passes Odor Test SAE J1351 Meets numerous other Auto Specs

Applications

- Nameplates
- Cost effective option for many LSE applications
- Attaching to powder coated and other LSE finishes
- Bonding to a variety of high and low surface energy materials such as ABS, powder coated paints, TPO, PE, PET, and more

Features

Acrylic Adhesive

74# Kraft Liner

Benefits

- Quick initial tack
- Low fogging, low flammability
- High peel and shear properties
- Excellent high and low temperature performance
- Conformable and good dimensional stability

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Adhesive Thickness	3 mils	0.076 mm	PSTC 133
Liner Thickness	5.5 mils	0.14 mm	PSTC 133
Loop Tack	125 oz/in	13.68 N/cm	PSTC 16
Static Shear (1" x 1" x 1 kg)	>7 Days		
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	-30 to 375 °F	-34 to 191 °C	
Recommended Storage Temperature	60 to 80 °F		
Recommended Storage Humidity	40 to 60 %		
Shelf Life (Standard)	12 Months		

Values shown are based on laboratory testing and represent typical product characteristics. Actual performance will vary depending on application conditions, and no guarantee of performance is made. The user is responsible for determining suitability for the intended application. No express or implied warranty, including merchantability or fitness for a particular purpose, is made.