



Acrylic Transfer Tape



Adhesive: Acrylic (I630)
Release Liner: 80# Polycoated Kraft
Specifications: Chrysler

Applications

- Permanent bonding to a variety of foam materials
- Mounting sound damping materials
- Screen print and nameplate applications

Features

Acrylic Adhesive

80# Kraft Liner

Benefits

- High tack adhesive
- Superior bond to a variety of foam substrates
- Excellent peel and shear properties
- Conformable and good dimensional stability

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Adhesive Thickness	3 mils	0.076 mm	PSTC 133
Liner Thickness	4 mils	0.102 mm	PSTC 133
Static Shear (1" x 1" x 1 kg)	>7 Days		
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	-30 to 220 °F	-34 to 104 °C	
Recommended Storage Temperature	60 to 80 °F		
Recommended Storage Humidity	40 to 60 %		
Shelf Life (Standard)	12 Months		