



Rubber Transfer Tape



Adhesive: Rubber (I917)
Release Liner: 74# Polycoated Kraft

Applications

- Laminating and bonding for urethane and polyethylene foams, felts, fabrics, and rigid plastics
- Permanent bonding in low-stress applications
- Ideal for temporary hold in place applications
- Automotive, graphic arts, HVAC, gasketing, and general bonding.

Features

Rubber Adhesive

74# Polycoated Kraft Liner

Benefits

- High peel strength
- Excellent initial tack
- Moderate shear strength
- Conformable and good dimensional stability

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Adhesive Thickness	1.4 mils	0.036 mm	PSTC 133
Liner Thickness	5.5 mils	0.14 mm	PSTC 133
Adhesion to Steel	144 oz/in	15.75 N/cm	PSTC 101 Mod - 1 mil PET
Loop Tack	160 oz/in	17.5 N/cm	PSTC 16
Static Shear (1" x 1" x 1 kg)	24 Hours		
Static Shear Air Side (1" x 1" x 1 kg)	24 Hours		
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	30 to 150 °F	-1 to 66 °C	
Recommended Storage Temperature	60 to 80 °F	15.6 to 26.7 °C	
Recommended Storage Humidity	40 to 60 %		
Shelf Life (Standard)	12 Months		

Values shown are based on laboratory testing and represent typical product characteristics. Actual performance will vary depending on application conditions, and no guarantee of performance is made. The user is responsible for determining suitability for the intended application. No express or implied warranty, including merchantability or fitness for a particular purpose, is made.